

Karam Shixaliyev ¹, Ibrahim Abbasov ², Khaver Sadig ³

¹ Department of Organic Substances and Technologies of High Molecular Connections, Azerbaijan State Oil and Industry University, Baku AZ1010, Azerbaijan, 20 Azadlig Avenue, E-mail: kerem_shixaliyev@mail.ru

² Department of Physics, Azerbaijan State Oil and Industry University, Baku AZ1010, Azerbaijan, 20 Azadlig Avenue, E-mail: ibrahimabbasov179@gmail.com

³ Department of Physics, Azerbaijan State Oil and Industry University, Baku AZ1010, Azerbaijan, 20 Azadlig Avenue, E-mail: sadig.xaver@gmail.com

THEORY AND PRACTICE OF OBTAINING COMPOSITE MATERIALS BASED ON POLYMER BLENDS

Received: May 22, 2019 / Revised: August 15, 2019 / Accepted: August 30, 2019

© Shixaliyev K., Abbasov I., Sadig Kh., 2019

Abstract. The regularities of the thermodynamic compatibility of various industrially produced polyolefins and heterochain polymers and the possibility of obtaining composite materials based on their mixtures with significantly increased performance properties based on existing production facilities and process equipment have been identified.

The methods have been developed for the chemical and physical modification of individual polymers, their mixtures to improve the performance properties of composite materials; including the method of modification of polyethylene, which made it possible to significantly increase its thermal stability in air and in vacuum, anti-corrosion properties.

The effectiveness of the use in composite materials of the petroleum resin PPC intended to produce the products operated under conditions of increased mechanical wear, temperatures, pressures and deformations.

Developed composite materials based on mixtures of PVC, TPU, CCPE+PVC, CCPE+PU, LDPE+BR, technology of their manufacturing and processing, application of new efficient products with extreme operating conditions: injection molded tires for agricultural machines, casing stabbing baskets, nuclear magnetic logging probes, scrapers and bucket elevators, sealing rings for pneumatic radiators, indented surface of the grain cleaning machines.

Keywords: compatibility, injection molded tires, processing, solubility parameter, chlorocarboxylated polyethylene (CCPE), polyvinyl chloride (PVC), composition, obtaining mixtures of polymers.

Introduction

The problem of obtaining polymer composites with the necessary properties for working under extreme conditions at the present time is solved in two ways: by synthesis new types of polymers and by creating polymer compositions, where the properties of the individual components additively complement each other.

The scientific and technological progress of manufacturing imposes more and new stringent requirements on the polymer products, and the demand of industry for new materials is constantly increasing. Thus, the development of various polymer composites, greatly simplifying the technology of their production and processing, reducing the cost of obtaining materials with the necessary sets of properties is extremely relevant under current technological conditions.

In the polymer industry there is large-tonnage production of individual polyolefins and heterochain polymers, on the one hand to permit the realization of a certain range of performance properties of polymer products, and on the other hand, the constant development of technology requires expanding the range of application of polymer products increasing their technical level. This contradiction put forward as one of

$$M = 12 \cdot 4 + 5 \cdot 1 = 53.$$

Then the solubility parameter of BR:

$$\delta_{BR} = \frac{0.92}{0.95} \cdot \frac{468}{53} + 0.05 \cdot \frac{415}{68} = 8.9.$$

The solubility parameter of LDPE:

$$\begin{aligned} \sum F &= 133; \\ M &= 1 \cdot 12 + 2 \cdot 1 = 14; \\ \delta_{LDPE} &= 0.96 \cdot \frac{133}{14} = 9.12. \end{aligned}$$

The calculation of the interaction parameter between polymers have been performed by the Hildebrand equation; R is the gas constant equal to $1,987 \text{ kcal/deg}^{-1}\text{mole}^{-1}$; T is the temperature in degrees Kelvin and V_r is the reference volume in cm^3/mole conveniently taken to be $100 \text{ cm}^3/\text{mole}$.

For this value of V_r and temperature 298 K, the Hildebrand equation takes the form:

$$\chi_{AB} = \frac{(\delta_A - \delta_B)^2}{G}.$$

In this case:

$$\chi_{BR-LDPE} = \frac{(9.12 - 8.9)^2}{6} = 0.081.$$

The following equation is used to calculate the critical $\chi_{BR-LDPE}$:

$$\chi_{cr} = \frac{1}{2} \cdot \left(\frac{1}{\chi_A^{1/2}} + \frac{1}{\chi_B^{1/2}} \right)^2,$$

which involves the degree of polymerization of each polymer in terms of the reference volume V_r . The degree of polymerization can be calculated based on the validity of the degree of polymerization χ , if the molar volume of the repeating unit of the polymer is known, by the equation:

$$\chi_A = \left(\frac{\bar{V}}{V_r} \right)_x.$$

A fairly good approximation is obtained from the relation:

$$\chi_A = \frac{M_A}{100},$$

where M_A is the molecular weight of polymer.

Thus, we have:

$$\begin{aligned} \chi_{BR} &= \frac{350000}{100} = 3500; \\ \chi_{LDPE} &= \frac{300000}{100} = 3000. \end{aligned}$$

Hence, using the equation for calculating the critical value

$$(\chi_{BR-LDPE})_{cr} = \frac{1}{2} \cdot \left(\frac{1}{3500^{1/2}} + \frac{1}{3000^{1/2}} \right)^2 = 6.18 \cdot 10^{-4}$$

we determine the probability of phase separation origin, for which purpose we calculate $\chi_{BR-LDPE}$ for various phase compositions. The results are summarized in Table 1.

As is clear, with a decrease in the concentration of any component in the mixture, the spinodal solubility parameter increases and LDPE dissolves in BR much better than BR in LDPE. The concentrations were determined by variational method at which absolute combination is possible. This is 0.08 wt % for LDPE and 0.06 wt % for BR.

Table 1

The solubility parameters of the BR-LDPE system

Φ_{BR}	$(\chi_{BR-LDPE})_{sp}$	Φ_{BR}	$(\chi_{BR-LDPE})_{sp}$
0.00	-	0.55	$6.3 \cdot 10$
0.05	$3.03 \cdot 10$	0.60	$6.55 \cdot 10$
0.10	$1.61 \cdot 10$	0.65	$6.96 \cdot 10$
0.15	$1.15 \cdot 10$	0.70	$7.60 \cdot 10$
0.20	$9.23 \cdot 10$	0.75	$8.57 \cdot 10$
0.25	$7.94 \cdot 10$	0.80	$1.01 \cdot 10$
0.30	$7.14 \cdot 10$	0.85	$1.28 \cdot 10$
0.35	$6.65 \cdot 10$	0.90	$1.83 \cdot 10$
0.40	$6.35 \cdot 10$	0.95	$3.48 \cdot 10$
0.45	$6.20 \cdot 10$	1.00	-
0.50	$6.19 \cdot 10$	-	-

Thus, the calculation method shows that the BR-LDPE system is practically incompatible.

To find the critical point of the system in the phase diagram, it is necessary to calculate the G_{mix} for different composition of the system. The calculation was performed at $T = 298$ K, the results of which have been summarized in Table 2.

Table 2

Heat of mixing BR-LDPE

Φ_{BR}	G_{mix}	Φ_{BR}	G_{mix}
0.00	-	0.55	$3.42 \cdot 10$
0.05	$6.58 \cdot 10$	0.60	$3.33 \cdot 10$
0.10	$1.25 \cdot 10$	0.65	$3.16 \cdot 10$
0.15	$1.77 \cdot 10$	0.70	$2.91 \cdot 10$
0.20	$2.22 \cdot 10$	0.75	$2.60 \cdot 10$
0.25	$2.60 \cdot 10$	0.80	$2.22 \cdot 10$
0.30	$2.91 \cdot 10$	0.85	$1.77 \cdot 10$
0.35	$3.16 \cdot 10$	0.90	$1.25 \cdot 10$
0.40	$3.33 \cdot 10$	0.95	$6.58 \cdot 10$
0.45	$3.42 \cdot 10$	1.00	-
0.50	$3.46 \cdot 10$	-	-

The calculated data show that the so-called symmetric case with the lower critical solution temperature (LCST) is observed for the BR-LDPE system. Based on the additivity principle, we have $T_{cr} = 503$ K.

Thus, from the above calculation conclusions can be drawn:

1. The BR-LDPE system is practically incompatible;
2. The combination is possible at the concentration of BR in LDPE up to 0.06 % and at the concentration of LDPE up to 0.08 %.

To compare the compatibility of polymer blends depending on the polarity of the components, the compatibility parameters for the system of polar components PVC and TPU were calculated (compared with the non-polar system LDPE-BR).

Compatibility calculation for the system polyvinyl chloride - thermoplastic polyurethane (PVC-TPU) at temperature 298 K

We calculate the solubility parameters of individual components of the mixture using tabular values of the Small molar attraction constants for different chemical groups, taking into account the density of

Theory and Practice of Obtaining Composite Materials Based on Polymer Blends

PVC at 298 K ($\rho = 1.41 \cdot 10^3 \text{ kg/m}^3$). In the calculation, we will consider the distribution of end groups due to the insignificance of their number and without taking into account the molecular weight distribution.

Unit link of PVC - $[-\text{CH}_2-\text{CHCl}-]_n$.

Molar constants of attraction:

$$-\text{CH}_2- \quad -\text{CH} = \text{Cl}-$$

$$\sum F = 133 + 28 + 270 = 431;$$

$$M = 12 \cdot 2 + 1 \cdot 3 + 35.5 = 62.5.$$

Then the solubility parameter of PVC will be:

$$\delta_{PVC} = 1.41 \cdot \frac{431}{62.5} = 9.72.$$

The solubility parameter of TPU, taking into account the fact that the density of TPU at 298 K is equal to $\rho_{298} = 1.1 \cdot 10^3 \text{ kg/m}^3$.

Unit link of TPU

$$[-(\text{CH}_2)_6-\text{OCOHN}-(\text{CH}_2)_4-]_n$$

$$-(\text{CH}_2)_6- \quad -\text{COO}- \quad -\text{NH}- \quad -(\text{CH}_2)_4$$

$$\sum F = 133 \cdot 6 + 310 + 180 + 133 \cdot 4 = 1820;$$

$$M = 12 \cdot 11 + 1 \cdot 21 + 16 \cdot 2 + 14 = 199;$$

$$\delta_{TPU} = 1.10 \cdot \frac{1820}{199} = 10.06.$$

The calculation of the interaction parameter between the polymers in the system is performed by the equation:

$$\chi_{AB} = \frac{V_r}{R \cdot T} \cdot (\delta_A - \delta_B)^2,$$

where R is the gas constant equal to $1.987 \text{ kcal/deg}^{-1} \text{ mole}^{-1}$; T is the temperature in degrees Kelvin and V_r is the reference volume in cm^3/mole conveniently taken to be $100 \text{ cm}^3/\text{mole}$. Thus, for $T = 298 \text{ K}$, the equation becomes:

$$\chi_{AB} = \frac{(\delta_A - \delta_B)^2}{G}.$$

In this case, for the system PVC-TPU we have:

$$\delta_{PVC-TPU} = \frac{(10.06 - 9.72)^2}{6} = 0.019.$$

To calculate the critical value $(\chi_{PVC-TPU})_{cr}$, the following equation is used:

$$\chi_{cr} = \frac{1}{2} \cdot \left(\frac{1}{\chi_A^{1/2}} + \frac{1}{\chi_B^{1/2}} \right)^2,$$

which involves the degree of polymerization of each polymer in terms of the reference volume V_r . The degree of polymerization can be calculated based on the validity of the degree of polymerization χ , if the molar volume of the repeating unit of the polymer is known, by the equation:

$$\chi_A = \left(\frac{\bar{V}}{V_r} \right)_x.$$

A fairly good approximation is obtained from the relation:

$$\chi_A = \frac{M_A}{100},$$

where M_A is the molecular weight of polymer.

Thus, we have:

$$\chi_{PVC} = \frac{90000}{100} = 900;$$

$$\chi_{TPU} = \frac{18000}{100} = 180.$$

Hence, using the equation for calculating the critical value

$$(\chi_{PVC-TPU})_{cr} = \frac{1}{2} \cdot \left(\frac{1}{(\chi_A(\Phi_A / G_p))^{1/2}} + \frac{1}{(\chi_B(\Phi_B)_{sp})^{1/2}} \right)^2$$

we determine the probability of phase separation origin, for which purpose we calculate $(\chi_{PVC-TPU})_{sp}$ for various phase compositions. The results are summarized in Table 3.

Table 3

Values of the spinodal interaction parameter for different phase compositions:

Item no.	PVC	$(\chi_{PVC-TPU})_{sp}$	Item no.	PVC	$(\chi_{PVC-TPU})_{sp}$
1.	0.00	-	12.	0.55	$6.67 \cdot 10^{-2}$
2.	0.05	$2.78 \cdot 10^{-3}$	13.	0.60	$7.18 \cdot 10^{-3}$
3.	0.10	$1.40 \cdot 10^{-2}$	14.	0.65	$7.87 \cdot 10^{-3}$
4.	0.15	$8.64 \cdot 10^{-3}$	15.	0.70	$8.79 \cdot 10^{-3}$
5.	0.20	$6.97 \cdot 10^{-3}$	16.	0.75	$1.01 \cdot 10^{-2}$
6.	0.25	$6.25 \cdot 10^{-3}$	17.	0.80	$1.19 \cdot 10^{-2}$
7.	0.30	$5.93 \cdot 10^{-3}$	18.	0.85	$1.46 \cdot 10^{-2}$
8.	0.35	$5.82 \cdot 10^{-3}$	19.	0.90	$1.92 \cdot 10^{-2}$
9.	0.40	$5.86 \cdot 10^{-3}$	20.	0.95	$2.84 \cdot 10^{-2}$
10.	0.45	$6.02 \cdot 10^{-3}$	21.	1.00	-
11.	0.50	$6.29 \cdot 10^{-3}$	-	-	-

Since 0.019 is significantly more than 0.006, that is $(\chi_{PVC-TPU}) > (\chi_{PVC-TPU})_{cr}$, then this system must be incompatible in a wide range of compositions. Using the equation

$$(\chi_{AB})_{sp} = \frac{1}{2} \cdot \left(\frac{1}{(\chi_A(\Phi_A)_{sp})^{1/2}} + \frac{1}{(\chi_B(\Phi_B)_{sp})^{1/2}} \right)^2 \quad (1)$$

we determine the probability of the phase separation origin, for which we calculate $(\chi_{PVC-TPU})_{sp}$ for different phase compositions.

As seen, TPU dissolves in PVC much better than PVC, and at a content of less than 10 % TPU, complete compatibility of the systems should be observed. The calculation shows that there is a so-called asymmetric case with two critical solution temperatures, the lower and the upper ones [12-16].

Preparation and study of compositions

Such compositions have a low relative elongation (100...200 % at 293 K), which is completely unsatisfactory for use in a number of RTG industries in particular for injection molded polyurethane tires manufacturing. For the purpose of imparting optimum technological and physical-mechanical properties to mixtures based on TPU, the modifying role of CCPE serving as a "carrier" for PVC incompatible with TPU was investigated.

The studies were conducted using 3² full factorial design (FFD). Homogenization was carried out by mixing of research components on a double-roller mixer at a temperature of 438 K for 15 minutes, then the

blades were injected which 7 days of exposure were subjected to rupture on a P-0.5 tensile testing machine according to GOST 270-75 at a drawing rate of 130 mm/min and a temperature of 293 K. Drawing on the literature data, optimal indicators for injection molded tires were determined: $d_v = 1.0 = 45.0$ kN/m is a tear resistance; $d_e = 1.0 = 375$ % is a relative elongation, where d_v and d_e – desired factor functions.

The relationship of the desirability coefficient y^1 with the desirability function has the form:

$$d = e^{-\left(y^1\right)^n},$$

where n is the exponent which value is determined by the requirement for the parameter.

Varying the indicator of desirability from -4 to $+4$, we define the type of regression equation that relates the current value of the studied indicator with the indicator of desirability, referring to the equation:

$$y_{\varepsilon}^1 = \alpha_0 + \alpha \cdot y^1,$$

where y^1 is the current value of the indicator.

The calculations found that:

$$y_{\varepsilon}^1 = -8.42 + 0.0276 \cdot y^1.$$

Taking the form of the desirability function $d = x / y^1$ according to [17-19], we determine the indicators of desirability for resistance to tearing y_{ε}^1 and relative elongation y^1 , as well as the corresponding functions of desirability. The results are summarized in Tables 4 and 5.

Table 4

Desirability function and desirability indicators for breaking strength and relative elongation

Item no.	y_{iG}^1	$d_i G$	$y_{i\varepsilon}^1$	$d_i \varepsilon$
1.	-2.78	0.01	4.78	1.0
2.	-3.40	0.01	0.37	0.45
3.	-2.97	0.01	-3.40	0.01
4.	-3.33	0.01	1.22	0.80
5.	-3.25	0.01	-3.23	0.01
6.	-3.67	0.01	0.81	0.61
7.	-2.99	0.01	-0.98	0.01
8.	-2.59	0.01	-1.73	0.50
9.	-2.84	0.01	-3.23	0.01
10.	-	-	-	-
11.	-3.84	0.01	-2.19	0.02
12.	-4.01	0.00	-3.01	0.01
13.	-3.01	0.01	-0.49	0.20
14.	-2.95	0.01	0.80	0.61
15.	-2.44	0.01	-2.69	0.01
16.	-2.74	0.01	-2.76	0.01
17.	-2.93	0.01	-2.41	0.01
18.	-3.16	0.01	-3.58	0.01

The generalized desirability function was determined by the formula:

$$D_i = \sqrt{d_i G \cdot \varepsilon}.$$

The results of the physical-mechanical tests of the obtained compositions and the generalized desirability function are shown in Table 5.

The analysis of tabular data shows that CCPE behaves as a typical polymeric plasticizer, due to the plasticizing effect of which the relative elongation of the composition increases by 2.5...5 times. The introduction of PVC enabled to reduce the negative impact of the plasticizing effect of CCPE on the breaking strength value.

An analysis of generalized desirability functions shows that:

1) an increase in the PVC content from 5 to 10 by pts. wt. leads to an increase in D_i from 0.067 to 0.078;

2) an increase in the content of CCPE from 5 to 20 by pts. wt. leads to D_i with an extremum at the level 12.5 pts. wt.

$X_2 = 5$ pts. wt., $D_i = 0.067$;

$X_2 = 12.5$ pts. wt., $D_i = 0.089$;

$X_2 = 20$ pts. wt., $D_i = 0.078$;

3) in one pair of the system (for example 3a, 2b, etc.) is maximum with an increased content of petroleum resin PPC.

To study the polymer mixtures a polarizing microscope MIN-8 equipped with a purpose made photo nozzle with a Zenit-TTL reflex camera with magnification $\times 480$, quartz wedge $L = \frac{1}{2}\lambda$ was used, polymer mixtures were studied at a temperature of 298 K.

Table 5

Physical-mechanical properties and generalized desirability function of the composition

Item no.	Variables				Responses			
	Temperature range, K	PVC	CCPE	PPC	Breaking strength, MPa, Y_0	Relative elongation, % Y_1	Remanent elongation, % Y_2	Generalized desirability function, D
	X_0	X_1	X_2	X_3				
1a 1	373	5.0	5.0	0.55	20.4	354	57.5	0.1
1b 2	373	5.0	5.0	2.2	18.2	477	89.5	0.067
2a 3	373	5.0	12.5	0.588	19.7	583	89.6	0.01
2b 4	373	5.0	12.5	2.35	18.4	453	81.3	0.089
3a 5	373	5.0	20.0	0.626	18.7	578	89.8	0.01
3b 6	373	5.0	20.0	2.5	17.2	510	77.1	0.078
4a 7	373	7.5	5.0	0.562	19.6	515	90.5	0.032
4b 8	373	7.5	5.0	2.25	21.1	536	87.4	0.071
5a 9	373	7.5	12.5	0.6	20.0	578	102.1	0.01
5b 10	373	7.5	12.5	2.4	-	-	-	-
6a 11	373	7.5	20.0	0.638	16.5	549	91.5	0.014
6b 12	373	7.5	20.0	2.55	15.9	572	106.4	0.00
7a 13	373	10.0	5.0	0.576	19.5	501	91.5	0.045
7b 14	373	10.0	12.5	2.3	19.8	465	80.0	0.078
8a 15	373	10.0	12.5	0.612	21.6	563	91.5	0.01
8b 16	373	10.0	12.5	2.45	20.5	565	84.4	0.01
9a 17	373	10.0	20.0	0.65	19.8	555	89.8	0.01
9b 18	373	10.0	20.0	2.6	19.1	588	89.6	0.01

Investigation of solubility and thermodynamic parameters of polymer mixtures by method of inverse gas chromatography and turbidimetric titration (in block and solution)

The solubility parameters of substances characterize the relationship between the mixing energy and mutual solubility. The value of the solubility parameter of the polymer is necessary to obtain valuable information about the behavior of the polymer when mixed with other polymers or low molecular weight substances. By Hildebrand's definition, the solubility parameter is defined as the square root of the cohesive energy density, that is, the evaporation energy per unit of volume.

Direct determination of the heat of vaporization, and hence the solubility parameters of polymers are impossible due to their non-volatility. Presently, methods for determining the cohesive energy of polymers

based on the examination of the interaction of a polymer-solvent with known solubility parameters became the most common.

The swelling of cross-linked polymers was studied in the research [20] and it was found that swelling is maximal in solvents that have the same cohesive energy density as the polymer. Bristow and Watson obtained the solubility parameters of polymers from measuring viscosity in a number of solvents using Flory-Huggins interaction parameters χ_{12} . Furthermore, the solubility parameter of the polymer was assumed to be equal to the solubility parameter of the solvent, in which the limiting viscosity is maximum.

Small obtained additive molar attraction constants for various molecular groups from measurements of the vapor pressure of volatile substances and used these values to calculate the solubility parameters of the polymers. Subsequently, these constants were revised by Hoy and Van Krevelen.

Sokh and Clark proposed to determine the cohesive energy density from the data of turbidimetric titration (TT) of solutions by polyprecipators. The solubility parameters of polystyrene and poly-o-chlorostyrene determined by them well correspond to the known values obtained from swelling measurements.

Ito and Gillet showed that when using polymers as the stationary phase and various sorbates with known solubility parameters, can be used inverse gas chromatography to determine the solubility parameters of polymers.

Both of the latter methods for determining the solubility parameters of polymers are characterized by the diametrically opposite state of the “polymer-solvent” system, namely, in the TT method the solubility parameter of the polymer is determined under conditions corresponding to the “infinite” dilution of the polymer in a solvent, which can be denoted as δ_2^0 . In the case of inversed gas chromatography, the solubility parameter is determined by the “infinite” dilution of the low molecular weight substance in the polymer and the maximum interaction between the polymer molecules. The solubility parameter is correctly designated as δ_2^∞ .

Therefore, considering the presence of strong specific intermolecular interactions in polar polymers, we should expect an increase in the difference between δ_2^0 and δ_2^∞ solvents and precipitators as the intermolecular interaction strength increases.

On the basis of Hildebrand-Scatchard and Flory theory, provided that the volume does not change when mixed, the parameter χ is related to the solubility parameter by the relation:

$$\chi = \frac{V_1}{R \cdot T} \cdot (\delta_1 - \delta_2)^2 + \chi_5 \quad (2)$$

where V_1 is the molar volume of the solvent; δ_1 and δ_2 are the solubility parameters of the solvent and the polymer, respectively; R , T are the gas constant and absolute temperature; χ_5 is the entropic contribution to the interaction parameters.

Opening brackets and dividing variables, we have:

$$\frac{\delta_1^2}{R \cdot T} - \frac{\chi}{V_1} = \frac{2 \cdot \delta_1 \cdot \delta_2}{R \cdot T} - \left(\frac{\delta_2^2}{R \cdot T} + \frac{\chi_5}{V_1} \right), \quad (3)$$

which is a linearized form of equation (2).

As established by Gray, the contribution of the χ/V term for good solvents (having least value χ for particular polymer) is insignificant and for these sorbates the linearization $\frac{\delta_1^2}{R \cdot T} - \frac{\chi}{V_1}$ relative to δ_1 is not very different from a parabola.

Accordingly, the polymer solubility parameter δ_i^∞ can be found from the slope of the linear dependence $\frac{\delta_1^2}{R \cdot T} - \frac{\chi}{V_1}$ relative to a number of sorbates. The values in the left-hand side of the equation

(3) can be found from the condition that samples in the vapor state behave like an ideal gas at infinite dilution. Then:

$$\delta_1 = \left(\frac{\Delta H_v - R \cdot T}{V_1} \right)^{0.5}.$$

Here the values of the molar volume of the solvent V_1 and the heat of evaporation ΔH_v are easily determined or are available in the literature [22; 23].

The Flory-Huggins interaction parameter is calculated using the equations proposed by Patterson and his co-workers

$$\ln \Omega^\infty = \ln \left(\frac{273.2 \cdot R}{P_1^0 \cdot V_g^0 \cdot M_1} - \frac{P_1^0}{R \cdot T \cdot (B_{ii} - V_1)} \right); \quad (4)$$

$$\chi_{12}^\infty = \ln \Omega^\infty - \ln \left(\frac{V_1}{V_2} - 1 + \frac{M_1 \cdot v_1}{M_2 \cdot v_2} \right),$$

where M_1 , P_1^0 , V_1 , v_1 are the molecular weight, saturated vapor pressure, molar and specific volumes of the solvent at temperature T , respectively; B_{ii} is the second virial coefficient; M_2 , v_2 are the molar weight of the segment and the specific volume of the polymer at T ; V_g^0 is the reduced to 273 K characteristic retention volume obtained in the usual way.

In return the values of χ in the case of titration with two different precipitants, one of which has a lower value δ_1 (χ_{CL}) and the other – a higher value of δ_1 (χ_{Ch}) will be:

$$\chi_{CL} = \frac{V_{mL} \cdot (\delta_2 - \delta_{mL})_{CL}^2}{R \cdot T} + (\chi_S)_{CL}; \quad (5)$$

$$\chi_{Ch} = \frac{V_{mh} \cdot (\delta_{mh} - \delta_2)_{Ch}^2}{R \cdot T} + (\chi_S)_{Ch} \quad (6)$$

Here the indices mL and mh are assigned to the mixture of solvent and precipitant at the turbidity point. Equating both expressions (5) and (6) to each other, taking $(\chi_S)_{CL} = (\chi_S)_{Ch}$ for a low concentration of the polymer in the solution and solving for δ_2^0 , we have:

$$\delta_2^0 = \frac{\sqrt{V_{mL} \cdot \delta_{mL}} + \sqrt{V_{mh} \cdot \delta_{mh}}}{\sqrt{V_{mL}} + \sqrt{V_{mh}}},$$

where

$$V_m = \frac{V_1 \cdot V_3}{\Phi_1 \cdot V_3 + \Phi_3 \cdot V_1};$$

$$\delta_m = \Phi_1 \cdot \delta_1 + \Phi_3 \cdot \delta_3.$$

Here Φ_1 and Φ_3 are the volume fractions of the solvent and precipitant in the solvent; δ_1 and δ_3 are the solubility parameters of the solvent and precipitant; V_1 , V_3 are molar volumes of the solvent and precipitant.

Thereby, the values δ_2^0 and δ_2^∞ can be determined from the experiment and, using the extrapolation method of reducing to the same temperature, we can compare them.

We have investigated industrial polymer samples, which were subjected to additional purification by reprecipitation of the wt % solution in an appropriate solvent in the precipitant – standard, with a solvent-precipitant relationship of 1:10.

As sorbates, solvents, and precipitators organic liquids of various chemical structures were used, the qualification was C.P.

Studies using the IGC method were performed on a Tsvet-100 gas chromatograph with a flame ionization detector. Nitrogen was used as carrier gas. A solid carrier was a silanized carrier Chromaton N-AW-DMCS with a particle diameter of 0.20–0.25 mm.

The nozzle was prepared by evaporation method. The solvents were: in the case of EPR – carbon tetrachloride, in the case of chlorocarboxylated LDPE (CCPE), chlorinated LDPE (CPE), PVC and PU – tetrahydrofuran. The percentage of stationary phase in the nozzle was determined by sequential weighing after 1 week of polymer extraction in a Soxhlet extractor. We used stainless steel columns with a length of 1.0 m, which were filled with nozzles containing polymers 10...12 wt %.

Characteristics of the columns are presented in Table 6.

Table 6

Characteristics of the columns

Polymer	Nozzle weight in the column, g	Polymer content in the nozzle, %	Polymer mass in the column, g
CCPE	5.750	10.0	0.575
CPE	4.520	10.1	0.558
PVC	5.750	10.3	0.592
PU	6.300	10.0	0.630
EPR	4.802	10.7	0.514

The experiments were carried out at 353, 373, 393 K, which is higher than the glass transition temperature of all polymers. The sorbate sample volume was 0.02...0.5 µl. The value of the retention time (δ interaction) was determined by gaseous methane.

Equilibrium values of retention volumes were obtained by extrapolation to zero flow rate of the gas-carrier.

For the solubility parameter of polymers, solutions with a concentration of 0.05 g/dl were prepared by the TT method. A precipitant was slowly added to the 15 ml polymer solution while stirring.

The change in the optical density of the solution was recorded on a photoelectric colorimeter FEC-M, after which the precipitator concentration corresponding to the beginning of the precipitation polymerization (turbidity point) was determined by extrapolation to zero optical density. For the titration of polymer solutions at 298 K, two different precipitants were used – one with a higher solubility parameter and the other with a lower solubility parameter.

Predictably, polar and non-polar chlorine derivatives of hydrocarbons turned out to be good solvents for CPE and CCPE.

Polar chlorinated hydrocarbon derivatives and ketones turned out to be good solvents for PU, and non-polar compounds for EPR. Notably, for all the polymers studied, tetrahydrofuran and chloroform proved to be good solvents at temperatures of 353...393 K. It is known [22; 23] that halogen atoms (or oxygen) activate a hydrogen atom and it becomes capable of forming hydrogen bonds, which are poorly realized between homogeneous molecules, what makes such compounds universal solvents of polymers. The small size of the molecules, which facilitates diffusion into the mass of the polymer is favorable for this.

After processing, the obtained values of $\frac{\delta_1^2}{R \cdot T} - \frac{\chi}{V_1}$ and δ_1 for different classes of sorbates (saturated hydrocarbons, chlorine-containing hydrocarbons, ketones, alcohols, etc.) were smoothed over the aggregate data set of the straight line $y = A + B \cdot X$, after which were calculated δ_2^∞ and the mean square error σ^2 . The results are summarized in Table 7.

The contribution of $\frac{\chi_{12}^\infty}{V}$ in $\frac{\delta}{R \cdot T} - \frac{\chi}{V_1}$ is different for a number of sorbates used, the value of which also varies with temperature.

The solubility parameters of polymers δ_2^0 and δ_2^∞

Polymer	δ_2^0			δ_2^∞	Experim. 298 K
	393 K	373 K	353 K	Calculation 298 K	
CCPE	6.75±0.31	7.26±0.49	7.75±0.33	9.16±0.36	9.86±0.35
CPE	7.11±0.49	7.53±0.56	7.93±0.44	9.06±0.50	9.91±0.35
PU	7.06±0.57	7.50±0.41	8.05±0.65	9.49±0.55	12.07±0.35
EPR	7.11±0.15	7.36±0.57	7.59±0.11	8.25±0.28	8.55±0.35
PVC	7.11±0.51	7.52±0.56	7.91±0.98	9.14±0.42	9.89±0.35

Therefore, by the criterion of the contribution χ/V_1 we selected for CCPE – 7 sorbates, PU – 7 sorbates, CPE – 6 sorbates and EPR – 7 sorbates, which were used to calculate δ_2^∞ .

As can be seen, all δ_2^∞ values are a decreasing function of temperature, which allows extrapolating the obtained results to 469 K with sufficient confidence [11-16].

The obtained value $\delta_2^\infty = 8.25 \pm 0.28$ for the EPR was in fairly good agreement with $\delta_2^\infty = 7.70 \pm 0.11$ obtained by the IGC method considering the influence of the nature and composition of the polymer on its solubility parameter.

It should be noted that the measurement error increases with an increase in the number of functional groups in the macromolecule, reaching a maximum value for PU.

It is demonstrated that in all cases the δ_2^0 values obtained from the titration data in aliphatic solvents are more widely scattered and consistently lower than the values obtained from the titration data in aromatic solvents. Hildebrand showed that good agreement with experiment can also be obtained for hydrocarbons if we assume that the values of their solubility parameters are 0.6 higher than those calculated from the evaporation energy. Nevertheless, an amendment to δ_1 of about 0.3 was practically required. This creates uncertainties in the value of δ_2^0 for aliphatic solvents leading however to an error in determining δ_2^0 not more than ± 0.35 . This value of the error was taken for all determinations of the solubility parameters of polymers by the method of TT.

The change in $\chi_{1(23)}^\infty$ with the composition for the CCPE-CPE-PVC systems is shown in Fig. 1.




Fig. 1. The change in $\chi_{1(23)}^\infty$ with the composition for the CCPE-CPE-PVC systems

Theory and Practice of Obtaining Composite Materials Based on Polymer Blends

There is a definite trend to increase the difference between δ_2^0 and δ_2^∞ denoted as $\Delta\delta_2^{0/\infty}$ as the number of polar groups increases.

Thus, if for a practically non-polar polymer – EPR the value $\chi_{1(23)}^\infty$ fits into the experimental error $\Delta\delta_2^{0/\infty}$, then for CCPE and CPE, which contain highly polar chloromethylene groups, the halogen of which is able to activate a hydrogen atom to form a hydrogen bond, the solubility parameters differ by an amount significantly higher than the instrumental error and $\Delta\delta_2^{0/\infty} = 0.7...0.8$. In the event of a highly polar PU polymer having a large amount of hydrogen bonds like NH...O, the difference in solubility parameters reaches a very large value $\Delta\delta_2^{0/\infty} = 2.58$ (for example: in the form of a dimer, acetic acid has $\delta_1 = 9.19$, while in the form of a monomer, $\delta_1 = 13.01$). The calculations are presented in Table 8.

Consequently, an experimental comparison of the values of solubility parameters of polymers, obtained by two methods IGC and TT, characterized by an extremely opposite state of the polymer in relation to the solvent, showed a significant difference in solubility parameters for polymers with strong specific interactions between macromolecules, which requires attention when using the solubility parameter theory to predict the compatibility of polymer pairs to the method by which the used value is obtained. It is apparent that for crystallizing polymers there should also be a difference in solubility parameters.

Thus, having determined two values of the solubility parameter by the TT and IGC method, it can be said that to predict the solubility parameter of such polymers as CCPE, CPE, PU, EPR and PVC, both of these values should be used [8–14].

Table 8

Calculation of solubility parameters of polymers with each other at different temperatures

Substance	393 K				473 K				353 K			
	CCPE	CPE	PU	EPR	CCPE	CPE	PU	EPR	CCPE	CPE	PU	EPR
Methanol	2.083	2.294	1.829	2.780	2.634	2.52	1.951	2.857	3.097	2.921	1.881	3.232
Etanol	2.057	2.225	2.038	2.291	2.272	2.311	1.462	2.333	2.892	2.644	1.734	2.712
Pentane	0.887	1.702	1.950	0.752	1.318	1.460	0.707	0.730	1.197	1.725	1.369	0.825
DEE	0.651	2.349	1.081	0.617	0.895	1.217	1.207	0.638	0.977	1.261	0.933	0.610
CP	0.746	2.112	0.809	0.526	0.819	0.892	0.543	0.452	0.883	0.883	0.436	0.530
Acetone	1.321	0.250	1.155	1.778	1.509	1.261	1.093	1.274	1.501	1.342	1.046	1.276
Hexane	0.566	1.649	1.713	0.809	1.331	1.237	1.539	0.812	1.298	1.761	1.463	0.837
EDC	0.947	1.114	0.917	0.553	0.987	1.160	0.795	0.262	1.038	1.137	0.792	0.457
CCl ₄	0.867	1.094	1.472	0.729	1.069	1.118	1.299	0.740	1.245	1.166	1.165	0.741
THF	0.647	0.923	0.949	0.543	0.678	0.754	0.829	0.522	0.756	0.725	0.709	0.362

With a view to examine the processing conditions of the compositions based on the studied polymers, work was done to determine the influence of the mixing temperature on the physicomechanical properties of the compositions: PVC+CCPE, TPU+PVC, BR+PVC+CCPE, TPU+PVC+CCPE+PPC.

The data obtained are shown in Tables 9, 10 and 11

Concerning question of reducing or raising the temperature, in the first case, along with a decrease in temperature, which is considered to be a desirable element in terms of processing, there is also a decrease in physical-mechanical parameters, moreover, the test film has an unattractive appearance, turbidity is observed and there is an attachment of unmelted polymer particles. As the temperature increases, processes of destruction develop, a reddening of the film is observed, which is explained by the formation of polyene segments in the PVC macromolecule.

Thus, the processing interval for PVC modified by chlorocarboxylate polyethylene should be considered as the temperature range between 416-423 K.

Reducing the concentration of the modifier leads to the loss of a number of valuable properties of modified PVC. The decrease in elasticity is observed and the incombustibility is lost. A preliminary

assessment of the PVC film prototypes on resistance to aggressive effects (sulfuric acid, hydrochloric acid), as well as a number of solvents indicates the favorable impact of the introduction of CCPE+PVC.

Table 9

Physical-mechanical properties of the developed composition based on PVC

Composition	Onset temperature, K	Breaking strength, MPa	Relative elongation, %	Residual elongation, %	Tear resistance, MPa
Original PVC	431	16.7	10.0	4.0	4.3
PVC+CCPE	463	18.7	20.0	12	5.9

Table 10

Physical-mechanical properties of composition based on PU

Item No.	Composition	Weight fraction	Breaking strength, MPa	Relative elongation, %
1.	PU	87	18	230
	PVC	10	-	-
	PPC	3	-	-
2.	PU	93	20	280
	PVC	5	-	-
	PPC	2	-	-
3.	PU	100	17	150

Table 11

Physical-mechanical characteristics of the developed compositions based on polyurethane (PU)

Parameter name	System, the ratio of components, weight fraction		
	PU+PVC+ CCPE 80:10:10	PU+PVC+ CCPE 70:10:20	PU+PVC+ CCPE 90:6:4
Tensile strength, MPa (kgf/cm ²)	42	38	36
Relative elongation, %	90	100	120
Combustibility	burns	burns	fades away
Breaking temperature, K	523	533	543

Conclusions

Based on the conducted study of the compatibility of polymers in various systems of thermodynamic, chemical and other features, we can point to the conclusion:

a) compositions based on TPU and PVC are used for the manufacture of molded tires, centralizers on the casing strings, pneumatic rings for pneumatic radiators, etc.;

b) compositions based on BR+PE+PVC+EPR+CCPE are recommended for production a nuclear (magnetic) logging probe, a tiering surface for grain cleaning machines, elevator buckets.

References

[1] F. A. Amirov, K. S. Shikhaliyev, U. T. Ahmadova, "Chemical Modification Of Oxidized Polymers", *International Journal of Development Research*, vol. 08, issue 07, pp. 21902–21906, July, 2018.

[2] K. S. Shikhaliyev, *Monomers for the synthesis of polymers*. Saarbrücken, Germany: Lambert Academic Publishing, 2017.

[3] K. S. Shikhaliyev, "Obtaining an ecological pure composition based on polyvinyl chloride and benzylnaphthanate ether obtained from Baku oil", in *Proc. Int. Conf. "World Science"*, Dubai, UAE, 2017, vol. 1, pp. 46–48.

[4] K. S. Shikhaliyev, "Exploited thermoplastics based compositions", *European Science Review*, issue 5–6, pp. 88–92, 2017.

[5] K. S. Shikhaliyev, N. A. Salimova, "Thermodynamics and mutual distribution of macromolecules in the systems: chlorine-chlorocontaining polymers", *European Science Review*, issue 3–4, pp. 118–119, 2017.

- [6] M. Forrest, "The Composition and Nature of Vulcanisation Fumes in the Rubber Industry – A Technical Review", *Progress in Rubber Plastics Recycling Technology*, vol. 31, issue 4, pp. 219–264, 2015.
- [7] Waleed A. Hussain, Abdullah A. Hussein, Jabar M. Khalaf, Ali H. Al-Mowali, Abdulwahab A. Sultan, "Dielectric Properties and a.c. Conductivity of Epoxy/Alumina Silicate NGK Composites", *Advances in Chemical Engineering and Science*, vol. 5, issue 3, pp. 282–289, 2015.
- [8] P. Sarkar, N. Modak, P. Sahoo, "Mechanical Characteristics of Aluminium Powder Filled Glass Epoxy Composites", *International Journal of Engineering and Technologies*, vol. 12, pp. 1–14, 2017.
- [9] K. Sai Sravani, B. Ram Gopal Reddy, Raffi Mohammed, "Effect of CaCO₃ and Al₂O₃ Fillers on Mechanical Properties of Glass/Epoxy Composites", *International Journal for Modern Trends in Science and Technology*, vol. 03, issue 06, pp. 207–213, June, 2017.
- [10] V. N. Kuleznev, P. V. Surikov, "Fazovyie ravnovesiya v trekhkomponentnykh smesyakh polimerov" ["Phase equilibria in ternary polymer blends"], *Vysokomolekulyarnyye soyedineniya. Seriya A [Polymer Science. Series A]*, vol. 54, no. 11, pp. 833–839, 2012. [in Russian].
- [11] M. Mulder, *Basic Principles of Membrane Technology*. Dordrecht, the Netherlands: Kluwer Academic, 1996.
- [12] N. A. Belov, A. P. Safronov, Y. P. Yampolskii, "Obrashchennaya gazovaya khromatografiya i termodinamika sorbtitsii v polimerakh" ["Inverse-gas chromatography and the thermodynamics of sorption in polymers"], *Vysokomolekulyarnyye soyedineniya. Seriya A [Polymer Science. Series A]*, vol. 54, no. 11, pp. 859–873, 2012. [in Russian].
- [13] I M. Arcana, B. Bundjali, I. Yudistira, B. Jariah, L. Sukria, Study on Properties of Polymer Blends from Polypropylene with Polycaprolactone and Their Biodegradability, *Polymer Journal*, vol. 39, no. 12, pp. 1337–1344, 2007.
- [14] E. A. Ermilova, A. A. Sizova, N. N. Il'icheva, D. V. Pleshakov, "Issledovaniye termodinamicheskoy sovmestimosti trekhkomponentnoy smesi nitraminov s sopolimerom metilmetakrilata i metakrilovoy kisloty" ["Investigation of thermodynamic compatibility of three components mixture of nitramine with copolymer methyl methacrylate and methacrylic acid"], *Uspekhi v Khimii i Khimicheskoy Tekhnologii [Success in Chemistry and Chemical Technology]*, vol. 28, issue 2 (151), pp. 65–67, 2014. [in Russian].
- [15] Yu. M. Zuyev, *Dostizheniya nauki i tekhnologii v oblasti reziny [Advances in Rubber Science and Technology]*. Moscow, Russia: Khimiia Publ., 1959. [in Russian].
- [16] A. E. Portyanskiy, Yo. Abrakham, G. L. Alizade, Ya. M. Bilalov, "Issledovaniye protsessa mekhanoinitsirovannoy modophikatsii SKEP s PVKH" ["Investigation of the process of mechanized initiation of EPDM with PVC"], *Azerbaydzhanskiy khimicheskii zhurnal [Azerbaijan Chemical Journal]*, no. 4, pp. 80–85, 1975. [in Russian].
- [17] O. A. Serenko, G. P. Goncharuk, et al., "Vliyaniye temperaturi na deformatsionnoye povedeniye kompozita na osnove plipropilena i chastits rezini" ["Effect of temperature on the stress-strain behavior of a polypropylene-particulate rubber composite"], *Vysokomolekulyarnyye soyedineniya. Seriya A [Polymer Science. Series A]*, vol. 49, no. 1, pp. 71–78, 2007. [in Russian].
- [18] I. Ya. Derikov, I. Yu. Kutergina, et al., "Stable nonequilibrium composites based on liquid-crystalline polymers and cadmium selenide nanoparticles", *Vysokomolekulyarnyye soyedineniya. Seriya A [Polymer Science. Series A]*, vol. 56, no. 4, pp. 488–497, 2014. [in Russian].
- [19] A. E. Zaikin, G. B. Bobrov, "Kompatibilizatsiya smesey nesovmestimikh polimerov napolneniyem" ["Compatibility of mixtures of incompatible polymers by filling"], *Vysokomolekulyarnyye soyedineniya. Seriya A [Polymer Science. Series A]*, vol. 54, no. 8, pp. 1275–1282, 2012. [in Russian].
- [20] S. H. El-Sabbagh, "Compatibility study of natural rubber and ethylene-propylene-diene rubber blends", *Applied polymer science*, vol. 90, no. 1, pp. 1–11, October, 2003.
- [21] A. A. Askadskii, "Vliyaniye silnikh mezhmolekulyarnikh i khimicheskikh vzaimodeystviy na sovmestimost polimerov" ["The effect of strong intermolecular and chemical interactions on the compatibility of polymers"], *Uspekhi khimii [Russian Chemical Reviews]*, 1999, vol. 68, no. 4, pp. 349–364. [in Russian].
- [22] A. Amash, R. H. Schuster, T. Früh, "Effects of compatibility in rubber/polypropylene blends", *Elastomere und Kunststoffe [Elastomers and Plastics]*, no.6, pp. 315–320, 2001.
- [23] M. O. Abou-Helal, S. H. El-Sabbagh, "Study on the compatibility of NR-EPDM blends using electrical and mechanical techniques", *Journal of Elastomers and Plastics*, vol. 37, no. 4, pp. 319–346, 2005.