

DOI

Andrii Klym¹, Yaroslav Blikharsky¹, Mariia Kyryliak², Yana Babii²

OVERVIEW OF DAMAGE FACTORS OF REINFORCED CONCRETE STRUCTURES AND THEIR IMPACT ON LOAD-BEARING CAPACITY

¹*Department of Highways and Bridges,*

²*Department of Building Construction and Bridges*

Lviv Polytechnic National University

andrii.b.klym@lpnu.ua

© Klym A., Blikharsky Y., Kyryliak M., Babii Y., 2025

This review analyzes key factors contributing to damage in reinforced concrete (RC) structures, including reinforcement corrosion, chemical attacks, cyclic and long-term mechanical loads, and extreme temperature effects. The study highlights crack formation as a primary damage mechanism, leading to structural degradation. Advanced computational modeling techniques, such as finite element analysis, offer valuable insights into crack propagation and corrosion processes but require further refinement. Future research should focus on developing high-performance materials, improving corrosion protection methods, and refining predictive models. Additionally, sustainable rehabilitation techniques and experimental validation of damage mechanisms are essential for enhancing the durability and serviceability of RC structures.

Keywords: Reinforced concrete (RC) structures, Cracking, Corrosion, Loading, Load-bearing Capacity, Durability.

Introduction

Reinforced concrete (RC) structures are widely used in construction due to their strength, durability, and versatility. However, over time, these structures are subject to various damaging factors that can reduce their load-bearing capacity, affecting their safety and longevity. The performance of RC structures is influenced by a multitude of factors, including mechanical stresses, environmental influences, and material degradation. Corrosion of reinforcement, thermal effects, and aggressive chemical attacks are some of the leading causes of damage that contribute to the deterioration of these structures.

In addition to physical and environmental factors, poor design, inadequate construction practices, and insufficient maintenance can exacerbate the damage to RC structures. These factors often lead to cracks, spalling, and, in extreme cases, catastrophic failure of structural components. As these issues evolve over time, it becomes increasingly important to assess and understand the causes of damage and the subsequent loss of load-bearing capacity.

This review aims to provide an in-depth analysis of the primary factors contributing to the damage and degradation of RC structures, while also highlighting recent advancements in research and innovative methods for assessing and preventing such damage. Emphasizing the need for proactive measures in the design and maintenance of RC structures, the study presents a comprehensive understanding of how various external and internal influences contribute to the failure mechanisms of reinforced concrete.

Given the widespread use of reinforced concrete in infrastructure, from bridges and buildings to dams and tunnels, understanding the mechanisms behind structural damage is crucial for improving the sustainability and safety of existing and future constructions. The findings of this review underscore the need for continued research and development of diagnostic techniques, materials, and preservation strategies to mitigate the risks associated with damage to RC structures. Furthermore, the insights gained from this analysis are integral to optimizing structural design, maintenance protocols, and rehabilitation

efforts, ensuring that RC structures can withstand both environmental and mechanical challenges over their operational lifespan.

Materials and methods

In modern construction of buildings and structures, the predominant share belongs to the use of reinforced concrete (RC) structures (Bobalo et al., 2019; Verma et al., 2014). RC plays a crucial role in fully utilizing strength indicators, creating various forms, ensuring fire resistance, durability, and economic efficiency. The use of RC allows for the creation of structures with high load-bearing capacity, capable of withstanding significant external loads (Vatulia et al., 2014). Over time, improvements in RC have made it a universal material for various construction applications and the implementation of different structural types.

RC owes its versatility to the synergy of its constituent materials: concrete withstands compressive loads, while steel reinforcement resists tensile stresses, both as working and structural reinforcement (Karpiuk et al., 2020). The first proposal to combine concrete with metal elements was made by French gardener Joseph Monier in the late 19th century to create garden pipes and planters (Meier, 1995). Over time, the idea of integrating these materials into a single system RC was rapidly adopted in bridge, building, and infrastructure construction (Meier, 1995). In 1886, François Hennebique first applied RC for constructing buildings and structures, and his innovative design approaches enabled the achievement of high-performance characteristics (Meier, 1995).

With each decade, research into the mechanical properties and behavior of RC under loads has increased significantly, leading to improved design and construction methods (Triantafillou, 1998). A crucial aspect today is the reliability and durability of RC structures, which can only be ensured through proper technical supervision and timely restoration work (Blikharskyi, 2021). High fire and corrosion resistance provide an additional level of safety and longevity for structures (Broomfield, 2007). The use of RC reduces construction costs, while innovative supplementary materials and advanced manufacturing technologies further enhance strength properties (Oehlers, 2004; Broomfield, 2007).

Modern research in the development of new materials and technologies, such as fiber-reinforced concrete, nanotechnologies, and polymer-based materials, opens new prospects for the modernization of RC structures, enhancing their strength, resistance to aggressive environments, and overall durability (Meier, 1995).

Over time, RC structures are subject to various types of damage and defects, potentially leading to failure under poor operational conditions (Bobalo et al., 2019). Damage primarily arises due to prolonged service life under mechanical and technological stresses, as well as exposure to aggressive environments (Rezaie et al., 2020; Klymenko & Polyanskyi, 2019).

Such damage and defects in RC structures reduce their load-bearing capacity, leading to reliability issues and decreased durability (Voskobiinyk, 2010; Chiu et al., 2019). Early detection and repair of damages are critical for ensuring the longevity of structures (Bazant, 1998). Research by Bastidas and (Bastidas, 2020) provides a detailed classification of damages and defects in RC structures caused by various factors. One such classification highlights technological influences, which include poor adherence to construction tolerances, improper concreting practices, violations of assembly requirements, and issues related to transportation and on-site installation (Blikharskyi & Kopiika, 2019).

One of the most common deficiencies is inadequate protective layer thickness, inaccuracies in geometric dimensions, and deviations in the physical and mechanical properties of materials (Blikharskyi, 2019; Blikharskyi, 2020).

The classification of damage is also addressed in regulatory engineering practices in Ukraine DSTU-N B V.1.2-18:2016 «Guidelines for the inspection of buildings and structures to determine and assess their technical condition» and in the European standard DCC-104 RILEM (RILEM TECHNICAL COMMITTEES, 1991). The effect of aggressive environments on concrete and reinforcement has been the focus of multiple studies, particularly in terms of damage occurring both in the zone of maximum moment

and across the entire cross-section (Fu et al., 2017; Smith, 2007). Structures in the chemical industry are particularly susceptible to such damage due to the high concentration of compounds that degrade RC.

A key observation made by various researchers is the gradual reduction in load-bearing capacity with increasing corrosion levels. Specifically on (Blikharsky, 2005) focuses on studying corrosion processes under simultaneous loading conditions and evaluating changes in the stress-strain state of RC structures under these conditions. In modern construction research, corrosion in RC structures remains a highly relevant issue. The primary consequences of corrosion include a reduction in the cross-sectional area of the steel reinforcement and damage to the compressed concrete zone. Such deterioration leads to an abrupt decline in the physical and mechanical properties of materials. Studies conducted by both Ukrainian and international researchers have provided assessments of the impact of corrosion damage on the actual load-bearing capacity of RC structures (Bastidas-Arteaga et al., 2009; Savitskyi, 2003; Mahmoodian, 2020).

The most destructive phase of corrosion occurs when reinforcement is exposed (Ye, 2013). This process follows a two-stage sequence: initially, aggressive substances (compounds) and air migrate through the pores and cracks in the concrete, reaching the steel reinforcement (Zhao et al., 2023; James et al., 2019; Angst, 2018). The next stage involves an active chemical corrosion process, during which corrosion products are formed on the reinforcement surface. The presence of moisture, oxygen, and various chemical compounds accelerates corrosion, leading to a reduction in the reinforcement's cross-sectional area (Malumbela et al., 2010; Xu et al., 2018).

Corrosion significantly impacts the load-bearing capacity of RC beams, particularly when the reinforcement cross-section decreases due to corrosion, as demonstrated in research by (Torres-Acosta et al., 2007). Corrosion processes have been examined in greater detail in studies by (Angst, 2018; Otieno et al., 2011), while the propagation of corrosion in crack zones is explored in (Lin, 1990).

A particularly important research area involves assessing the influence of corrosion on the stress-strain state of RC structures. Studies by (Yuan et al., 2024; Peng et al., 2024) suggest that one of the most effective solutions to this issue is the use of special concrete additives to enhance the necessary physical and mechanical properties. For example, (Song et al., 2019) developed a superhydrophobic concrete (S-concrete) coating with a sliding angle of $6.5 \pm 0.5^\circ$ and a contact angle of $160 \pm 1^\circ$. This coating provides high mechanical strength at a low cost while maintaining superhydrophobic properties even after scratching or abrasion. Moreover, S-concrete demonstrates excellent anti-icing properties and high corrosion resistance, making it practical for use in specific regions.

Another research direction involves establishing the relationship between corrosion levels and crack formation in RC structures, as cracking is a critical factor in the corrosion process of reinforcement bars (Corral-Higuera et al., 2011; Mundra et al., 2017). In a study by (Fursa et al., 2017), a promising method for assessing corrosion damage was proposed, where the primary indicator of corrosion intensity is the width of cracks.

Since RC consists of two materials (concrete and steel), their joint performance is crucial and depends on the bond between them. Corrosion weakens this bond, ultimately reducing the overall load-bearing capacity of the structure (Gu et al., 2018). The contact between concrete and reinforcement plays a vital role in ensuring proper adhesion. A study by (Chen et al., 2019) examined the effects of key concrete design parameters including the water-to-cement ratio, concrete cover thickness, and aggregate size on the microstructure of the reinforcement-concrete interface.

Corrosion of reinforcement and concrete leads to crack formation, and in advanced stages, it can cause spalling of concrete layers. This is considered one of the most critical damage types due to its negative impact on the stress-strain state of RC structures (Chrysafi et al., 2017; Pozzer et al., 2021). Cracks in RC structures arise not only over time due to loading but also from various other factors. They may originate during the manufacturing stage or develop during operation. The primary causes include improperly designed reinforcement frameworks, insufficient concrete cover, excessive prestressing force, technological influences, shrinkage deformations, as well as environmental and thermal effects (Patel and Peralta, 2017).

A study by (Khiem and Toan, 2014) derived a Rayleigh coefficient considering an arbitrary number of cracks and developed a simplified sequential tool for modal analysis of cracked structures. Other studies (Ercolani et al., 2018; Khiem and Toan, 2014) highlight that the key parameter governing stress redistribution in structures is crack width. Numerical modeling of cracks in software systems has made it possible to predict crack formation and its impact on the stress-strain state of RC structures (Cohen et al., 2018; Kwan and Ma, 2016). In another study (Nuguzhinov et al., 2020), analytical expressions were obtained to determine the external bending moment and pre-stresses at which normal cracks form perpendicular to the axis. This allows for assessing the load-bearing capacity of RC structures at the design stage according to both limit state groups and evaluating their actual technical condition in service.

Research on the residual load-bearing capacity of RC beams with existing damage has been explored in various studies. Experimental results indicate that the deformation behavior of flexural elements is highly dependent on defects and damage, particularly in the compressed concrete zone. Damage in this region leads to a reduction in the ultimate strain of concrete and causes a shift in the neutral axis (Klymenko and Polyanskyi, 2019).

RC structures subjected to bending experience significant loads during operation. Special attention is given to damage in the compressed concrete zone, as defects in this region can lead to serious structural problems and a reduction in overall load-bearing capacity. The primary factors affecting damage in the compressed zone include technological influences, mechanical loads, aggressive environments, and chemical factors.

Mechanical loads, particularly long-term loading, are among the most common causes of damage to the compressed concrete zone in flexural RC structures. Research by (Bazant, 1998) indicates that sustained loading causes concrete creep, leading to microcrack formation and a reduction in the strength of the compressed concrete fibers. Cyclic loading accelerates material fatigue, resulting in progressive microcracking and initiating a stepwise deterioration process in concrete (Fatemi and Yang, 1998).

Developed (Golos and Ellyin, 1987) a method that incorporates both crack initiation and propagation stages. Their damage criterion is based on the concept of cumulative strain energy density as a key damage parameter. The effect of mean stress on damage accumulation is also incorporated into this formulation. Furthermore, the influence of loading sequence was investigated using a novel testing setup that enables precise control over stress states and fracture zones. Their stepwise deformation modeling approach accounts for load sequence effects, predicting fatigue life and the complete evolution of deformation under cyclic loading.

Aggressive environments, particularly the presence of sulfates, chlorides, and acids, significantly impact the condition of the compressed concrete zone. Corrosion of reinforcement due to chloride penetration or carbonation-induced deterioration leads to crack formation in concrete, reducing its strength (Broomfield, 2007). This study presents an innovative poromechanics based model for analyzing concrete subjected to low temperatures, incorporating nanoscale length-scale effects and a comprehensive review of alkali-aggregate reaction modeling in concrete.

Another major environmental factor affecting RC structures is freeze-thaw cycles, which contribute significantly to concrete degradation. Developed (Fagerlund, 1977) found that these cycles induce microcracks in concrete, leading to its progressive deterioration. To mitigate this issue, additional admixtures should be incorporated into concrete during manufacturing, especially for structures exposed to open environmental conditions.

Chemical agents such as sulfates and acids contribute to the chemical degradation of concrete. Sulfate penetration into the concrete pores and depth leads to the formation of ettringite, which initially causes expansion and, over time, results in the destruction of the compressed concrete zone (Gollop and Taylor, 1992; Santhanam and Cohen, 2002). Investigated key aspects of sulfate attack on concrete and proposed monitoring methods along with modeling criteria for sulfate-induced damage (Santhanam and Cohen, 2002). Acid exposure also negatively affects RC structures by dissolving the cement matrix, which accelerates crack formation and expansion in concrete (Taylor et al., 2001).

A reduction in the load-bearing capacity of RC structures also occurs due to temperature effects, whether excessively high or low (Hibner, 2017). In fire conditions, concrete suffers damage to its protective layer, leading to a decrease in overall strength and deformation parameters (Broomfield, 2007). Temperature fluctuations induce thermal expansion and contraction of concrete, causing thermal cracking. High temperatures, in particular, contribute to the degradation of concrete structure and a reduction in structural load-bearing capacity (Hlavička et al., 2024; Zhou et al., 2024).

Examined the effect of temperature on concrete spalling and provided recent findings suggesting that spalling should not occur under certain conditions, emphasizing the need to account for it during structural design (Hager, 2013). Fire-induced concrete spalling damages the cross-section and significantly reduces the structural load-bearing capacity.

Nowadays, computational modeling is widely used to study damage in RC structures. Employed non-traditional finite element methods to model fiber-reinforced RC beam-columns (Wang et al., 2013). The study demonstrated that modeling allows for predicting the formation and progression of microcracks in concrete. Developed (Lee et al., 2016) a simulation program for chloride attack, incorporating a two-dimensional finite element method to predict chloride ion penetration. Each discretized element in the finite element model was treated as an independent object capable of storing necessary parameters and autonomously calculating chloride content values, facilitating the simulation of failure in critical regions. The findings indicate that the deterioration of reinforcement due to corrosion in RC structures is significantly influenced not only by the damaged concrete but also by the structural geometry, which plays a crucial role in the overall degradation process.

Results and Discussion

The analysis of damage mechanisms in reinforced concrete (RC) structures highlights the significant impact of various physical, chemical, and mechanical factors on their durability and load-bearing capacity. Corrosion of reinforcement and concrete degradation due to environmental exposure lead to progressive cracking, spalling, and ultimately structural failure. Among the primary causes, improper reinforcement design, inadequate concrete cover, excessive pre-stressing forces, and technological defects during construction contribute to early damage initiation. Moreover, shrinkage-induced deformations, atmospheric and temperature influences further exacerbate the degradation of RC structures over time.

One of the most critical aspects affecting structural integrity is the formation and propagation of cracks, which not only weaken the structure but also serve as pathways for aggressive agents such as chlorides, sulfates, and carbon dioxide. These chemical agents penetrate the concrete matrix, triggering reinforcement corrosion and causing expansive reactions, such as ettringite formation, which lead to further deterioration. Additionally, exposure to cyclic loading induces fatigue-related microcracks, progressively reducing the structure's strength. Long-term mechanical loads contribute to creep deformations, affecting the stiffness and serviceability of RC elements.

Fire exposure and extreme temperature variations also have a profound impact on the stability of RC structures. At elevated temperatures, concrete undergoes thermal expansion, spalling, and degradation of its mechanical properties, leading to a significant reduction in load-bearing capacity. Cold-weather conditions, particularly freeze-thaw cycles, accelerate crack formation and contribute to concrete disintegration. This necessitates further exploration of advanced concrete mixtures incorporating supplementary cementitious materials and chemical admixtures to improve resistance against thermal effects and environmental degradation.

Computational modeling has proven to be an essential tool for predicting damage evolution in RC structures. Advanced finite element models allow for the simulation of crack initiation, chloride penetration, and fatigue damage progression, providing a valuable framework for assessing structural reliability. However, existing models require further refinement to incorporate multi-scale deterioration mechanisms, including nanomechanical interactions and microstructural changes in concrete due to aggressive environments.

Conclusions

Given the extensive damage mechanisms identified in RC structures, future research should focus on:

1. Development of Advanced Materials – Investigating high-performance concrete mixtures with self-healing properties, fiber reinforcement, and nano-additives to enhance resistance against chemical and mechanical degradation.
2. Enhanced Corrosion Protection Strategies – Implementing innovative protective coatings, cathodic protection methods, and chloride-resistant reinforcement materials to extend the service life of RC structures.
3. Refinement of Computational Models – Developing multi-scale numerical models that integrate deterioration kinetics, chemical diffusion processes, and mechanical damage evolution to improve predictive accuracy.
4. Experimental Validation of Damage Mechanisms – Conducting large-scale laboratory and field tests to analyze the long-term behavior of RC structures under real-world loading and environmental conditions.
5. Sustainable Rehabilitation Techniques – Exploring eco-friendly restoration methods, such as bio-based repair materials and low-carbon cement alternatives, to minimize environmental impact while enhancing structural resilience.

By addressing these critical research gaps, future advancements in material science, structural engineering, and computational modeling will contribute to the development of more durable and sustainable RC structures capable of withstanding complex environmental and mechanical stressors.

Acknowledgments

This work was supported by the National Research Foundation of Ukraine (Grant No. 2023.05/0026).

References

- Angst, U. M. (2018). Challenges and opportunities in corrosion of steel in concrete. *Materials and Structures*, 51(4), 1–20. <https://doi.org/10.1617/s11527-017-1131-6>
- Bastidas, D. M., & Bastidas, J. M. (2020). Corrosion of reinforced concrete structures. *Frontiers in Materials*, 7, 170. <https://doi.org/10.3389/fmats.2020.00170>
- Bastidas-Arteaga, E., Bressollette, P., Chateauneuf, A., & Sánchez-Silva, M. (2009). Probabilistic lifetime assessment of RC structures under coupled corrosion–fatigue deterioration processes. *Structural Safety*, 31(1), 84–96. <https://doi.org/10.1016/j.strusafe.2008.04.001>
- Bazant, Z. P., & Planas, J. (1998). *Fracture and size effect in concrete and other quasibrittle materials*. CRC Press. <https://doi.org/10.1201/9780203756799>
- Blikharskyy, Y. (2020). Calculation of damage RC constructions according to deformation model. *Theory and Building Practice*, 2(2), 99–106. <https://doi.org/10.23939/jtbp2020.02.099>
- Blikharskyy, Y. (2021). Experimental results of damaged RC beams. *Theory and Building Practice*, 3(1), 100–105. <https://doi.org/10.23939/jtbp2021.01.100>
- Blikharskyy, Y. Z., & Kopiika, N. S. (2019). Research of damaged reinforced concrete elements, main methods of their restoration and strengthening. *Resource-Saving Materials, Structures, Buildings and Structures*, 37, 316–322. http://nbuv.gov.ua/UJRN/rmkbs_2019_37_40
- Blikharskyy, Y. Z., & Kopiika, N. S. (2021). Comparative analysis of approaches to assessing the reliability of building structures. *Ukrainian Journal of Construction and Architecture*, 3, 46–55. <https://doi.org/10.30838/J.BPSA.CEA.2312.010721.46.766>
- Blikharskyy, Z. Ya. (2005). *Stress-strain state of reinforced concrete structures in an aggressive environment under load* (Doctoral dissertation), Kyiv <https://uacademic.info/en/document/0505U000494>

- Bobalo, T., Blikharsky, Y., Kopiika, N., & Volynets, M. (2019). Serviceability of RC beams reinforced with high strength rebar's and steel plate. *Lecture Notes in Civil Engineering*, 47, 25–33. https://doi.org/10.1007/978-3-030-27011-7_4
- Broomfield, J. P. (2007). *Corrosion of steel in concrete: Understanding, investigation and repair*. CRC Press. <https://doi.org/10.1201/9781003223016>
- Chen, F., Li, C. Q., Baji, H., & Ma, B. (2019). Effect of design parameters on microstructure of steel-concrete interface in reinforced concrete. *Cement and Concrete Research*, 119, 1–10. <https://doi.org/10.1016/j.cemconres.2019.01.005>
- Chiu, C. K., Sung, H. F., Chi, K. N., & Hsiao, F. P. (2019). Experimental quantification on the residual seismic capacity of damaged RC column members. *International Journal of Concrete Structures and Materials*, 13(1), 1–22. <https://doi.org/10.1186/s40069-019-0338-z>
- Chrysafi, A. P., Athanasopoulos, N., & Siakavellas, N. J. (2017). Damage detection on composite materials with active thermography and digital image processing. *International Journal of Thermal Sciences*, 116, 242–253. <https://doi.org/10.1016/j.ijthermalsci.2017.02.017>
- Cohen, M., Monteleone, A., & Potapenko, S. (2018). Finite element analysis of intermediate crack debonding in fibre reinforced polymer strengthened reinforced concrete beams. *Canadian Journal of Civil Engineering*, 45(10), 840–851. <https://doi.org/10.1139/cjce-2017-0439>
- Corral-Higuera, R., Arredondo-Rea, S. P., Neri-Flores, M. A., Gómez-Soberón, J. M., Calderón, F. A., Castorena-González, J. H., & Almaral-Sánchez, J. L. (2011). Sulfate attack and reinforcement corrosion in concrete with recycled concrete aggregates and supplementary cementing materials. *International Journal of Electrochemical Science*, 6(3), 613–621. [https://doi.org/10.1016/S1452-3981\(23\)15020-6](https://doi.org/10.1016/S1452-3981(23)15020-6)
- Ercolani, G. D., Felix, D. H., & Ortega, N. F. (2018). Crack detection in prestressed concrete structures by measuring their natural frequencies. *Journal of Civil Structural Health Monitoring*, 8, 661–671. <https://doi.org/10.1007/s13349-018-0295-2>
- Fagerlund, G. (1977). The significance of critical degrees of saturation at freezing of porous and brittle materials. *Durability of Building Materials*, 2(3), 217–225. <https://lup.lub.lu.se/search/files/4759429/1553671.pdf>
- Fatemi, A., & Yang, L. (1998). Cumulative fatigue damage and life prediction theories: A survey of the state of the art for homogeneous materials. *International Journal of Fatigue*, 20(1), 9–34. [https://doi.org/10.1016/S0142-1123\(97\)00081-9](https://doi.org/10.1016/S0142-1123(97)00081-9)
- Fu, C., Jin, N., Ye, H., Jin, X., & Dai, W. (2017). Corrosion characteristics of a 4-year naturally corroded reinforced concrete beam with load-induced transverse cracks. *Corrosion Science*, 117, 11–23. <https://doi.org/10.1016/j.corsci.2017.01.002>
- Fursa, T. V., Dann, D. D., Petrov, M. V., & Lykov, A. E. (2017). Evaluation of damage in concrete under uniaxial compression by measuring electric response to mechanical impact. *Journal of Nondestructive Evaluation*, 36(2), Article 30. <https://doi.org/10.1007/s10921-017-0411-y>
- Gollop, R. S., & Taylor, H. F. W. (1992). Microstructural and microanalytical studies of sulfate attack. I. Ordinary Portland cement paste. *Cement and Concrete Research*, 22(6), 1027–1038. [https://doi.org/10.1016/0008-8846\(92\)90033-R](https://doi.org/10.1016/0008-8846(92)90033-R)
- Golos, K., & Ellyin, F. (1987). Generalization of cumulative damage criterion to multilevel cyclic loading. *Theoretical and Applied Fracture Mechanics*, 7(3), 169–176. [https://doi.org/10.1016/0167-8442\(87\)90032-2](https://doi.org/10.1016/0167-8442(87)90032-2)
- Gu, X., Guo, H., Zhou, B., Zhang, W., & Jiang, C. (2018). Corrosion non-uniformity of steel bars and reliability of corroded RC beams. *Engineering Structures*, 167, 188–202. <https://doi.org/10.1016/j.engstruct.2018.04.020>
- Hager, I. (2013). Behaviour of cement concrete at high temperature. *Bulletin of the Polish Academy of Sciences: Technical Sciences*, 61, 145–154. http://psjd.icm.edu.pl/psjd/element/bwmeta1.element.oai-journals-pan-pl-83679/c/oai-journals-pan-pl-83679_full-text_paper_13.pdf
- Hibner, D. R. (2017). *Residual axial capacity of fire exposed reinforced concrete columns* (Master's thesis). Michigan State University. <https://www.proquest.com/openview/928d94f115983c0c02629b4754e7710c/1?pq-origsite=gscholar&cbl=18750>
- Hlavička, V., Biró, A., Tóth, B., & Lublőy, É. (2024). Fire behaviour of hollow core slabs. *Construction and Building Materials*, 411, Article 134143. <https://doi.org/10.1016/j.conbuildmat.2023.134143>
- James, A., Bazarchi, E., Chiniforush, A. A., Aghdam, P. P., Hosseini, M. R., Akbarnezhad, A., & Ghodoosi, F. (2019). Rebar corrosion detection, protection, and rehabilitation of reinforced concrete structures in coastal

- environments: A review. *Construction and Building Materials*, 224, 1026–1039. <https://doi.org/10.1016/j.conbuildmat.2019.07.250>
- Karpiuk, V., Somina, Y., & Maistrenko, O. (2020). Engineering method of calculation of beam structures inclined sections based on the fatigue fracture model. In *Proceedings of CEE 2019: Advances in Resource-saving Technologies and Materials in Civil and Environmental Engineering 18* (pp. 135–144). Springer International Publishing. https://doi.org/10.1007/978-3-030-27011-7_17
- Khiem, N. T., & Toan, L. K. (2014). A novel method for crack detection in beam-like structures by measurements of natural frequencies. *Journal of Sound and Vibration*, 333(18), 4084–4103. <https://doi.org/10.1016/j.jsv.2014.04.031>
- Klymenko, Y. V., & Polyanskyi, K. V. (2019). Experimental studies of the stress-strain state of damaged RC beams. *Bulletin of Odessa State Academy of Civil Engineering and Architecture*, 76, 24–30. http://nbuv.gov.ua/UJRN/Vodaba_2019_76_5
- Kwan, A. K. H., & Ma, F. J. (2016). Crack width analysis of reinforced concrete under direct tension by finite element method and crack queuing algorithm. *Engineering Structures*, 126, 618–627. <https://doi.org/10.1016/j.engstruct.2016.08.027>
- Lee, S., Kim, T., Suh, K., Bae, Y., Kim, H., & Lee, J. (2016). Analysis of repair times of marine reinforced-concrete structures considering shape effects and domain discontinuity. *Transactions of the ASABE*, 59(3), 975–982. <https://doi.org/10.13031/trans.59.11342>
- Lin, S. H. (1990). Chloride diffusion in a porous concrete slab. *Corrosion (USA)*, 46(12), 961–967. <https://doi.org/10.5006/1.3585052>
- Mahmoodian, M. (2020). Structural reliability assessment of corroded offshore pipelines. *Australian Journal of Civil Engineering*, 1–11. <https://doi.org/10.1080/14488353.2020.1816639>
- Malumbela, G., Alexander, M., & Moyo, P. (2010). Variation of steel loss and its effect on the ultimate flexural capacity of RC beams corroded and repaired under load. *Construction and Building Materials*, 24(6), 1051–1059. <https://doi.org/10.1016/j.conbuildmat.2009.11.012>
- Meier, U. (1995). Strengthening of structures using carbon fibre/epoxy composites. *Construction and Building Materials*, 9(6), 341–351. [https://doi.org/10.1016/0950-0618\(95\)00071-2](https://doi.org/10.1016/0950-0618(95)00071-2)
- Mundra, S., Criado, M., Bernal, S. A., & Provis, J. L. (2017). Chloride-induced corrosion of steel rebars in simulated pore solutions of alkali-activated concretes. *Cement and Concrete Research*, 100, 385–397. <https://doi.org/10.1016/j.cemconres.2017.08.006>
- Nuguzhinov, Z., Vatin, N., Bakirov, Z., Khabidolda, O., Zholmagambetov, S., & Kurokhtina, I. (2020). Stress-strain state of bending reinforced beams with cracks. *Magazine of Civil Engineering*, 96(5), 1–15. <https://doi.org/10.18720/MCE.97.1>
- Oehlers, D. J., & Seracino, R. (2004). *Design of FRP and steel plated RC structures: Retrofitting beams and slabs for strength, stiffness and ductility*. CRC Press. <https://books.google.com.ua/books?hl=uk&lr=&id=NuzKo34NRYkC&oi=fnd&pg=PP1>
- Otieno, M. B., Beushausen, H. D., & Alexander, M. G. (2011). Modelling corrosion propagation in reinforced concrete structures – A critical review. *Cement and Concrete Composites*, 33(2), 240–245. <https://doi.org/10.1016/j.cemconcomp.2010.11.002>
- Patel, J., & Peralta, P. (2017). Characterization of deformation localization mechanisms in polymer matrix composites: A digital image correlation study. In *International Digital Imaging Correlation Society*. Springer, Cham. (pp. 243–246). https://doi.org/10.1007/978-3-319-51439-0_58
- Peng, H., Chen, Z., Liu, M., Zhao, Y., Fu, W., Liu, J., & Tan, X. (2024). Study on the effect of additives on the performance of cement-based composite anti-corrosion coatings for steel bars in prefabricated construction. *Materials*, 17(9), 1996. <https://doi.org/10.3390/ma17091996>
- Pozzer, S., Rezazadeh Azar, E., Dalla Rosa, F., & Chamberlain Pravia, Z. M. (2021). Semantic segmentation of defects in infrared thermographic images of highly damaged concrete structures. *Journal of Performance of Constructed Facilities*, 35(1), 04020131. [https://doi.org/10.1061/\(ASCE\)CF.1943-5509.0001541](https://doi.org/10.1061/(ASCE)CF.1943-5509.0001541)
- Rezaie, A., Achanta, R., Godio, M., & Beyer, K. (2020). Comparison of crack segmentation using digital image correlation measurements and deep learning. *Construction and Building Materials*, 261, 120474. <https://doi.org/10.1016/j.conbuildmat.2020.120474>
- RILEM Technical Committees. (1991). Damage classification of concrete structures. *Materials and Structures / Matériaux et Constructions*, 24, 253–259.

- Santhanam, M., Cohen, M. D., & Olek, J. (2002). Sulfate attack research—whither now? *Cement and Concrete Research*, 32(6), 831–836. [https://doi.org/10.1016/S0008-8846\(01\)00510-5](https://doi.org/10.1016/S0008-8846(01)00510-5)
- Savitskyi, M. V. (2003). Fundamentals of reliability calculation, durability, and constructive-technological design of reinforced concrete structures in aggressive environments. *Collection of Scientific Papers: Building Structures*, 2(59), 235–240.
- Smith, R. W. (2007). *The effects of corrosion on the performance of reinforced concrete beams* (Master's thesis). Ryerson University. https://rshare.library.torontomu.ca/articles/thesis/The_effects_of_corrosion_on_the_performance_of_reinforced_concrete_beams/14656110?file=28137951
- Song, J., Li, Y., Xu, W., Liu, H., & Lu, Y. (2019). Inexpensive and non-fluorinated superhydrophobic concrete coating for anti-icing and anti-corrosion. *Journal of Colloid and Interface Science*, 541, 86–92. <https://doi.org/10.1016/j.jcis.2019.01.014>
- Taylor, H. F. W., Famy, C., & Scrivener, K. L. (2001). Delayed ettringite formation. *Cement and Concrete Research*, 31(5), 683–693. [https://doi.org/10.1016/S0008-8846\(01\)00466-5](https://doi.org/10.1016/S0008-8846(01)00466-5)
- Torres-Acosta, A. A., Navarro-Gutierrez, S., & Terán-Guillén, J. (2007). Residual flexure capacity of corroded reinforced concrete beams. *Engineering Structures*, 29(6), 1145–1152. <https://doi.org/10.1016/j.engstruct.2006.07.018>
- Triantafillou, T. C. (1998). Shear strengthening of reinforced concrete beams using epoxy-bonded FRP composites. *ACI Structural Journal*, 95(2), 107–115. https://www.researchgate.net/profile/Thanasis-Triantafillou/publication/247509718_Shear_Strengthening_Of_Reinforced_Concrete_Beams_Using_Epoxy-Bonded_FRP_Composites/links/5a8aecb20f7e9b1a9554c8c4/Shear-Strengthening-Of-Reinforced-Concrete-Beams-Using-Epoxy-Bonded-FRP-Composites.pdf
- Vatulia, G., Orel, Y., & Kovalov, M. (2014). Carrying capacity definition of steel-concrete beams with external reinforcement under the fire impact. *Applied Mechanics and Materials*, 617, 167–170. <https://doi.org/10.4028/www.scientific.net/AMM.617.167>
- Verma, S. K., Bhadauria, S. S., & Akhtar, S. (2014). Probabilistic evaluation of service life for reinforced concrete structures. *Chinese Journal of Engineering*, 2014, 1–8. <https://doi.org/10.1155/2014/648438>
- Voskobiinyk, O. P. (2010). Typological comparison of defects and damages of reinforced concrete, metal, and composite beam structures. *Bulletin of Lviv Polytechnic National University*, 662, 97–103.
- Wang, Y. H., Nie, J. G., & Cai, C. S. (2013). Numerical modeling on concrete structures and steel-concrete composite frame structures. *Composites Part B: Engineering*, 51, 58–67. <https://doi.org/10.1016/j.compositesb.2013.02.035>
- Xu, F., Xiao, Y., Wang, S., Li, W., Liu, W., & Du, D. (2018). Numerical model for corrosion rate of steel reinforcement in cracked reinforced concrete structure. *Construction and Building Materials*, 180, 55–679. <https://doi.org/10.1016/j.conbuildmat.2018.05.215>
- Ye, H., Tian, Y., Jin, N., Jin, X., & Fu, C. (2013). Influence of cracking on chloride diffusivity and moisture influential depth in concrete subjected to simulated environmental conditions. *Construction and Building Materials*, 47, 66–79. <https://doi.org/10.1016/j.conbuildmat.2013.04.024>
- Yuan, S., Zhao, X., Jin, Z., Zhao, Q., Fan, L., Deng, J., & Hou, B. (2024). Design and realization of versatile durable fluorine-free anti-corrosive coating with robust superhydrophobicity. *Electrochimica Acta*, 495, Article 144428. <https://doi.org/10.1016/j.electacta.2024.144428>
- Zhao, L., Wang, J., Gao, P., & Yuan, Y. (2023). Experimental study on the corrosion characteristics of steel bars in concrete considering the effects of multiple factors. *Case Studies in Construction Materials*, 20, Article e02706. <https://doi.org/10.1016/j.cscm.2023.e02706>
- Zhou, H., Tian, X. Q., Wang, Y. S., Lin, H. L., & Chen, H. H. (2024). Experimental investigation of damage and failure modes in stirrupless reinforced concrete beams under varied thermal-mechanical loadings. *Journal of Structural Engineering*, 150(3), Article 04023240. <https://doi.org/10.1061/JSENDH.STENG-12990>

А. Б. Клим¹, Я. З. Бліхарський¹, М. В. Кириляк², Я. С. Бабій²

¹Національний університет “Львівська політехніка”,
Кафедра автомобільних доріг та мостів

²Національний університет “Львівська політехніка”,
Кафедра будівельних конструкцій та мостів

ОГЛЯД ФАКТОРІВ ПОШКОДЖЕННЯ ЗАЛІЗОБЕТОННИХ КОНСТРУКЦІЙ ТА ЇХ ВПЛИВ НА НЕСУЧУ ЗДАТНІСТЬ

© Клим А. Б., Бліхарський Я. З., Кириляк М. В., Бабій Я. С., 2025

Залізобетонні конструкції зазнають впливу численних факторів пошкодження, що безпосередньо впливають на їхню несучу здатність і довговічність. Основними причинами пошкоджень є корозія арматури, тріщиноутворення, механічні навантаження, вплив агресивного середовища, температурні коливання та довготривалі експлуатаційні процеси. Корозія арматури, спричинена проникненням хлоридів або карбонізацією, призводить до тріщин і руйнування бетонного прошарку, що змінює напружено-деформований стан конструкцій. Циклічні навантаження та повзучість бетону зумовлюють поступову деградацію матеріалу та виникнення мікротріщин, що в довгостроковій перспективі знижує несучу здатність конструкцій. Додатково, негативний вплив мають агресивні середовища, зокрема сульфатна і кислотна атака, які спричиняють хімічну корозію бетону, що в результаті порушує його структуру. Високі температури, особливо під час пожежі, викликають втрату міцності бетону через руйнування його мікроструктури та спонтанне відколювання. Аналіз сучасних досліджень показує, що комп'ютерне моделювання пошкоджень є ефективним інструментом для прогнозування процесів деградації та розробки підходів до їх мінімізації. Визначено, що використання методів кінцевих елементів дозволяє враховувати широкий спектр чинників та точно оцінювати вплив пошкоджень на стан конструкцій. У статті проведено огляд основних механізмів та причин руйнування залізобетонних конструкцій та їхнього впливу на несучу здатність, що дозволяє краще розуміти і оцінювати процеси, що відбуваються в матеріалах під дією експлуатаційних навантажень. Отримані результати аналізу досліджень можуть бути використані для вдосконалення методів проектування та розробки ефективних стратегій (технологій) для підсилення, відновлення і ремонту залізобетонних конструкцій.

Ключові слова: Залізобетонні (RC) конструкції, тріщини, корозія, навантаження, несуча здатність, довговічність.